

R-TECH[®]

FF

FANFOLD WALL INSULATION

BY INSULFOAM

PREMIUM FIRE RATED RIGID INSULATION

Description

R-Tech Fanfold (FF) is an engineered rigid insulation consisting of a superior closed-cell, lightweight and resilient expanded polystyrene (EPS) with advanced polymeric laminate facers. R-Tech FF is available with factory adhered metallic-reflective facers, white facers or a combination of the two. The core of R-Tech FF is the same high-quality EPS as our InsulWall brand insulations and meets or exceeds the requirements of ASTM C578, Type I, Standard Specification for Rigid Cellular Polystyrene Thermal Insulation. In addition, R-Tech FF has excellent dimensional stability, compressive strength and water resistance properties. R-Tech is an ENERGY STAR[®] qualified insulation and can contribute towards LEED[®] credits.

Uses

R-Tech FF has been used successfully for numerous commercial, industrial and residential applications. The following are examples of the many R-Tech FF applications:

- Siding Underlayment
- Basement Walls
- Cavity Walls
- Crawl Spaces
- Interior Walls
- Waterproofing Protection Board
- Gable-Ends

Advantages

- **Labor Savings.** R-Tech FF is available in 100 ft² (one-square) and 200 ft² (two-square) bundles, and is lightweight enough that the average contractor can carry 400 ft² at one time.
- **Environmentally Friendly.** R-Tech FF does not contain any ozone-depleting blowing agents, may contain recycled material and the foam core is 100% recyclable.
- **Stable R-value.** The product's thermal properties will remain stable over its entire service life. There is no thermal drift, so the product is eligible for an Insulfoam 20-Year Thermal Performance Warranty.
- **Water Resistance.** R-Tech facers provide a surface that is virtually impervious to moisture.
- **Insect and Mold Resistance.** R-Tech can be manufactured with an inert additive that deters termites and carpenter ants. R-Tech FF does not sustain mold and mildew growth.
- **Jobsite Durability.** With a polymeric facer on either side of it, R-Tech is extremely flexible and durable.

THE PROVEN STANDARD FOR WALLS.



- **Cost Effective.** R-Tech FF is typically less expensive than comparable insulation products.
- **Enhanced R-values.** In certain applications, increased R-values can be obtained by placing the metallic reflective side of the R-Tech towards a dead air space. R-value gain is dependent on the amount of dead air space between the R-Tech and outer surface. R-value gains are based on the ASHRAE Handbook of Fundamentals. See Effective R-value chart on reverse side.

Sizes

R-Tech FF is packaged accordian-style and is available in one- and two-square bundles. R-Tech Fanfold is available in thicknesses of 1/4", 3/8", 1/2" and 3/4" and has a standard nominal density of 1 pcf. Individual panel sizes within the fanfold bundle are 2' x 4'. Different densities are available upon request.

Installation Recommendations

Please refer to the appropriate R-Tech application sheets for recommended installation procedures.

INSULATION ENGINEERED TO MAKE A DIFFERENCE.

Typical Physical Properties of R-Tech Fanfold*

Property	Type I	Test Method
Nominal Density (pcf)	1.0	ASTM C303
C-Value (Conductance) BTU/(hr•ft ² •°F)		
(per inch) @ 25° F	.23	ASTM C518
@ 40° F	.24	or
@ 75° F	.26	ASTM C177
R-value (Thermal Resistance) (hr•ft ² •°F)/BTU		
(per inch) @ 25° F	4.35	ASTM C518
@ 40° F	4.2	or
@ 75° F	3.9	ASTM C177
Compressive Strength (psi, 10% deformation)	13	ASTM D1621
Strength (psi)	33	ASTM C203
Dimensional Stability (maximum %)	< 2%	ASTM D2126
Water Vapor Transmission (perms)	< 1.0	ASTM E96
Absorption (% vol.)	< 1.0	ASTM C272
Capillarity	none	–
Flame Spread	< 20	ASTM E84
Smoke Developed	150 - 300	ASTM E84

*Properties are based on data provided by resin manufacturers, independent test agencies and Insulfoam.

Effective R-values^a (metallic-reflective facer and dead air space)

R-Tech Thickness	Design Temp.	Effective R-value (R-Tech MR + Air Space) _b
1/4"	25° F	3.90
	40° F	3.85
	75° F	3.80
3/8"	25° F	4.50
	40° F	4.40
	75° F	4.30
1/2"	25° F	5.00
	40° F	4.90
	75° F	4.80
3/4"	25° F	6.10
	40° F	5.90
	75° F	5.70

a Effective R-values determined using InsulWall I. Higher density InsulFoam products will provide higher R-values. The type of construction application and the depth of the air space will also impact the actual Effective R-value.

b Requires 0.75" - 3.50" dead air space and the R-Tech MR facer towards the dead air space.